

In the Claims:

1. **(currently amended):** A pigment, comprising  
(A) optionally a layer consisting of a metal,  
(B) at least one layer, which is located between the layers (A) and (C), if a layer (A) is present, and consists of the metal, silicon (Si) and oxygen (O), and  
(C) optionally a layer consisting of  $\text{SiO}_z$  on layer (B), wherein  $0.70 \leq z \leq 2.0$ , ~~especially  $1.10 \leq z \leq 2.0$ , more especially  $1.40 \leq z \leq 2.0$ .~~
2. **(currently amended):** A pigment according to claim 1, comprising  
(B) at least one layer, which consists of the metal, silicon (Si) and oxygen (O), and  
(C) at least one layer consisting of  $\text{SiO}_z$  on layer (B), wherein  $0.70 \leq z \leq 2.0$ , ~~especially  $1.10 \leq z \leq 2.0$ , more especially  $1.40 \leq z \leq 2.0$ .~~
3. **(currently amended):** The pigment according to claim 1 ~~or 2~~, comprising  
(C1) a layer consisting of  $\text{SiO}_z$ ,  
(B) at least one layer, which is located between the layers (C1) and (C2), and consists of the metal, silicon (Si) and oxygen (O),  
(C2) at least one layer consisting of  $\text{SiO}_z$  on layer (B), wherein  $0.70 \leq z \leq 2.0$ , ~~especially  $1.10 \leq z \leq 2.0$ , more especially  $1.40 \leq z \leq 2.0$ .~~
4. **(currently amended):** The pigment according to claim 3, comprising  
(D) an additional layer of a material having a high index of refraction, ~~especially  $\text{TiO}_2$ , amorphous carbon, diamond-like carbon, or silicon carbide.~~
5. **(currently amended):** The pigment according to claim 4, comprising  
(D1) a layer of a material having a high index of refraction, especially  $\text{TiO}_2$ ,  
(C1) a layer consisting of  $\text{SiO}_z$ ,  
(B) at least one layer, which is located between the layers (C1) and (C2), and consists of the metal, silicon (Si) and oxygen (O),  
(C2) a layer consisting of  $\text{SiO}_z$ , and  
(D2) a layer of a material having a high index of refraction, ~~especially  $\text{TiO}_2$ , wherein  $0.70 \leq z \leq 2.0$ , especially  $1.10 \leq z \leq 2.0$ , more especially  $1.40 \leq z \leq 2.0$ .~~

6. **(currently amended):** The pigment according to ~~any of claim [[s]] 1, to 5,~~ wherein the metal is selected from Ag, Al, Cu, Cr, Mo, Ni, Ti, or alloys thereof, ~~especially aluminum.~~
7. **(currently amended):** The pigment according to claim 3 having the following layer structure:  $\text{TiO}_2/\text{SiO}_2/\text{core}/\text{SiO}_2/\text{TiO}_2$ , wherein the core is formed of a layer (B) or of a layer (B)/layer (A)/layer (B), wherein the layer (B) is present on the plane-parallel faces, but not the side faces of layer (A), wherein the  $\text{SiO}_2$  layer is only present on the plane-parallel faces, but not the side faces and the  $\text{TiO}_2$  layer is applied to the whole surface;  $\text{SiC}/\text{SiO}_2/\text{core}/\text{SiO}_2/\text{SiC}$ , or  $\text{C}/\text{SiO}_2/\text{core}/\text{SiO}_2/\text{C}$ , wherein  $0.70 \leq z \leq 2.0$ , ~~especially  $1.10 \leq z \leq 2.0$ , more especially  $1.40 \leq z \leq 2.0$ .~~
8. **(currently amended):** A pigment, ~~obtainable~~ obtained by calcination of plane-parallel structures (flakes), comprising (A) at least one layer consisting of a metal and (C) at least one layer consisting of  $\text{SiO}_2$  with  $0.70 \leq z \leq 2.0$ , ~~especially  $1.1 \leq z \leq 2.0$ ,~~ in a non-oxidizing atmosphere and optionally coating of the obtained flakes with further layers.
9. **(currently amended):** Plane-parallel structures, comprising (A) a layer consisting of a metal, ~~especially aluminum,~~ and (C) at least one layer consisting of  $\text{SiO}_2$ , wherein  $0.70 \leq z \leq 2.0$ , ~~especially  $1.10 \leq z \leq 2.0$ , more especially  $1.40 \leq z \leq 2.0$ .~~
10. **(cancelled).**
11. **(currently amended):** A textile, coating, paint, printing ink, plastic, G composition, cosmetic preparation, or a glaze for ceramic and glass, comprising a pigment according to ~~any of claim [[s]] 1, to 8.~~
12. **(cancelled).**
13. **(new):** A pigment according to claim 1, wherein  $1.40 \leq z \leq 2.0$ .
14. **(new):** A pigment according to claim 2, wherein  $1.40 \leq z \leq 2.0$ .

15. **(new):** The pigment according to claim 4, wherein the material comprising the additional layer (D) having a high index of refraction is selected from the group consisting of  $\text{TiO}_2$ , amorphous carbon, diamond like carbon and silicon carbide.
16. **(new):** A pigment according to claim 5, wherein  $1.40 \leq z \leq 2.0$ .
17. **(new):** The pigment according to claim 5, wherein the material comprising layers (D1) and (D2) is  $\text{TiO}_2$ .
18. **(new):** A pigment according to claim 9, wherein the metal of layer (A) is aluminum.
19. **(new):** A pigment according to claim 9, wherein  $1.40 \leq z \leq 2.0$ .
20. **(new):** A textile, coating, paint, printing ink, plastic, composition, cosmetic preparation, or a glaze for ceramic and glass, comprising a pigment according to claim 2.
21. **(new):** A textile, coating, paint, printing ink, plastic, composition, cosmetic preparation, or a glaze for ceramic and glass, comprising a pigment according to claim 8.
22. **(new):** A textile, coating, paint, printing ink, plastic, composition, cosmetic preparation, or a glaze for ceramic and glass, comprising a pigment according to claim 13.